



THE R. J.  
**MARSHALL**  
COMPANY

26776 W. Twelve Mile Rd.  
Southfield, MI 48034-7807  
248/353-4100  
toll free USA 800/338-7900  
Fax 248/948-6460  
www.rjmarshall.com

# Technical Information

## Pulpro Series

Near White Calcium Carbonate

### Chemical Properties (Typical)

<u>Grade:</u>	<u>PP-3</u>	<u>PP-8</u>	<u>PP-10</u>	<u>PP-20</u>
CaCO <sub>3</sub> (%)	95	95	95	95
MgCO <sub>3</sub> (%)	2	2	2	2

### Physical Properties (Typical)

<u>Grade:</u>	<u>PP-3</u>	<u>PP-8</u>	<u>PP-10</u>	<u>PP-20</u>
Specific Gravity	2.71	2.71	2.71	2.71
Free Moisture (%)	<0.2	<0.2	<0.2	<0.2
Loose Bulk Density (lb/ft <sup>3</sup> )	30	47	47	N/A
Average Particle Size (microns)	3.2	7.5	10	22

Revised September 28, 2009

**Terms and Conditions of Sale:** All statements, technical information and recommendations are based on tests we believe to be reliable, the accuracy or completeness is not guaranteed, and the following is made in place of all warranties, expressed or implied. Our only obligation is to replace product proved to be defective. We shall not be liable for any injury, loss or damage, direct or indirect, from using or not being able to use the product. Before using, customer must determine the suitability of the product for the intended use and customer assumes the responsibility. This statement may not be changed except by an agreement signed by an officer of The R.J. Marshall Company.