



Spray Granite Advantage



Spray Granite Advantage is shipped as a non-hazardous, non-flammable material and will last indefinitely if properly stored. Spray Granite Advantage is available in standard colors with a minimum order size of 1-gallon. Custom colors and color matching is available upon request.

Colors may vary slightly. Appearance can be altered with change in catalyzation, backfill pigmentation and surface treatment. Final product determination must be based on spraying in your process.





Spray Granite Advantage filler system is an economical alternative to solid surface and cultured granite castings. It is designed to be mixed into a clear gelcoat and sprayed behind a clear gelcoat or against the mold as the primary wear surface. Spray Granite Advantage can be used in cast polymer and fiberglass reinforced plastic products. It is made from the highest UV stable thermoset polyester resin and ATH fillers available.

- Outstanding coverage and hide properties
- Less shrinkage than thermal plastic granule products
- Superior bonding with your quality gelcoat system
- Easier sanding and less finishing time as compared to thermal plastic granule products
- Superior hardness, stain resistance and thermal shock performance
- The ability to mix only what you need when you need it (mix today, spray today)
- Extraordinary cost savings when compared to other "wet" ready-to-spray products

Spray Granite Advantage Suggestions For Use

Spray Granite Advantage Large (SGL):

SGL incorporates granules as large as 10 mesh to create a more chunky appearance like solid surface or natural granite. Like SGA, SGL has been developed to build opacity quickly which improves cost efficiency. This material needs to be evaluated for use in your application and equipment. Some systems will not handle the larger granules. We suggest that molds be pre-wet with gel coat before spraying these products through dry spray equipment to maximize transfer efficiency and minimize the chance for porosity on the surface of the part.

Equipment:

Spray Granites can be effectively applied with a cup gun and a #9 nozzle (9/32 inch orifice). For larger volume applications, MarPro equipment offers a dry spray and a volume wet spray system. If the spray equipment plugs, either try a larger orifice or add more gelcoat to the mix.

Filler/ Resin Ratio:

This product should be mixed into a good quality clear gelcoat at a ratio of 60% gelcoat to 40% filler. It is essential that a gelcoat be used to provide the proper thixotrophy and ultraviolet light stability. Thixotrophy values of 5 or higher will hold granules in place on vertical surfaces. The opacity of the matrix is provided by the granite effect particulate only, so the filler loading should remain as high as possible.

Catalyst Levels:

The catalyst levels used should be based on recommendations from your gelcoat or catalyst supplier. If you are using a cup gun to spray the granites you may want to consult your gelcoat manufacturer about the minimum catalyst levels to give you additional working time. Do not go below the minimum catalyst level your gelcoat manufacturer recommends.

Matrix Consistency:

Since every gelcoat is different, the mix ratios will vary. If the granules bounce off the mold when you spray, the mix is too thick. If the granules sag or the granite layer does not become opaque the mix needs additional filler.

Background Color/ Color Additives:

The background color of the Spray Granite Advantage is provided by the combination of it's colored granule concentrates. Pigmentation can be used to alter it if the granite is to be sprayed behind a gelcoat. Some care must be taken in pigmenting non-gel coated parts if the surface is going to be sanded after spraying. In these cases, most of the pigmented color will be lost, as a greater granule surface area will be exposed, diminishing the visible pigmented resin which had covered the surface.

Overflows- Spraying under the overflows is particularly difficult. Make sure that extra care is taken to get good coverage in that area.

Backsplashes- The granules will stop the backsplashes from closing tightly. Make sure the area where the backsplash door fits up against the mold is well taped before spraying. Remove the tape and all granules that might stop a snug fit before closing the backsplash door.

Thermal Cycling- SGA makes certified cast polymer parts. For a superior product, use it behind gelcoat with 10% Prolite 700C in the backfill matrix to make a part that surpasses 1000 cycles.



toll free: 800-338-7900 customer care: 888-514-8600 www.rjmarshall.com salesinfo@rjmarshall.com