

Technical Information



The R.J. Marshall Co

26776 W. Twelve Mile Rd.
Southfield, MI 48034-7807
248-353-4100
800-338-7900
Fax 248-948-6460
Order Desk 888-514-8600
Order Fax 877-717-5577
www.rjmarshall.com

CS265X Calcium Sulfate Filler System

CS265X is a ground dihydrate grade of calcium sulfate containing 20.1% water of hydration. The waters of hydration provide good flame and smoke suppression in a variety of room temperature cured thermoset composite applications.

Chemical Properties (Typical)

CaSO ₄ -2H ₂ O	97% min
Combined Moisture	20.10%
Free Moisture	0.1%

Physical Properties (Typical)

Specific Gravity	2.32
Mohs Hardness	2.0
+50 mesh	0%
+100 mesh	1%
+200 Mesh	9%
+325 Mesh	28%

Note: Gypsum is a naturally occurring mineral and is not a color controlled product. Shifts in color are to be expected in this product.

Revised 8/20/13

Terms and Conditions of Sale: All statements, technical information and recommendations are based on tests we believe to be reliable, the accuracy or completeness is not guaranteed, and the following is made in place of all warranties, expressed or implied. Our only obligation is to replace product proved to be defective. We shall not be liable for any injury, loss or damage, direct or indirect, from using or not being able to use the product. Before using, customer must determine the suitability of the product for the intended use and customer assumes the responsibility. This statement may not be changed except by an agreement signed by an officer of The R.J. Marshall Company.