



SPRAY GRANITE REFERENCE SHEET

Coverage

1. ~.60lbs (275grams) Total mix per Ft² (+overspray)
2. ~2.5 cups Per 31" top w/bowl
3. ~2.0 cups Per 31" top wo/bowl
4. ~3.0 cups Per 48" x 24" Board (8 Ft²)

Approximate volume formula for cup spray mix (rounded)

Cup	Ratio
1.00c SGA per cup	2 part SGA per cup
2.00c Gel coat per cup	3 part Gel coat per cup

Spray Equipment



Model 100 cup gun
order# G100

FN-8 tip (6.2mm)

order# G200-8

FN-9 tip (7.1mm)

order# G200-9

Paper cups, 32oz - case/500
order# G2001



Kobalt spray gun
Medium 6.0mm
Large 8.0mm

Dry spray system



**GS Granite
spray system**



Pressure pot system



**Binks 7N
gun**

Spray Granite Advantage Cup spray mix

SGA/SGL/SCT products

450 grams	Gel Coat	60%
300 grams	SGA	40%
<hr/>		
750 grams		100%

4.5 grams Catalyst 1%

Spray Granite Extreme Cup spray mix

SGE products

472 grams	Gel coat	63%
278 grams	SGE	37%
<hr/>		
750 grams		100%

4.7 grams Catalyst 1%

SGE 285 Empire, SGE 306 Sequoia

525 grams	Gel coat	70%
225 grams	SGE	30%
<hr/>		
750 grams		100%

5.3 grams Catalyst 1%

Spray granite filler and sprayed color chip samples are available. Model 100 cup gun, tips and paper cups also available. Please visit us at Rjmarshall.com or call toll free 800-338-7900 for details.

If the spray equipment plugs: try a larger orifice, drill air intake hole larger on cup gun lid or add more gel coat to the mix. A pigmented backpour matrix or gel coat back coat that matches the spray granite color is recommended for best color results. Note, a change in background color can have an effect on the final appearance of spray granite products.

26776 W. Twelve Mile Road, Southfield, MI 48034
toll free: 800-338-7900 customer care: 888-514-8600
www.Rjmarshall.com salesinfo@rjmarshall.com