

PE (Polyethylene Pulp) 254SL

Typical Properties

Specific Gravity	2.7
Fiber length (mm):	0.5 - 0.8
Fiber diameter (um):	5
Free Moisture:	1.7%
Bulk Density (lbs/gal)	3.46
Bulk Density (lbs/ft ³)	25.9
Loss on ignition (LOI)	8.72%
Polyethylene Pulp (%)	100

PE 254SL expanded Polyethylene Pulp is a rapidly dispersing fibrous filler that is designed for high water and oil absorption. PE 254SL is designed specifically to improve crack resistance, slump, trowelability, viscosity, water retention, and workability. PE 254SL offers very low shrinkage upon drying for a variety of building products. PE 254SL has excellent chemical resistance to all common solvents including the most aggressive ketones and esters, alkalis and acids, bleaches and detergents.

APPLICATIONS: PE 254SL is specifically designed as a reinforcing fiber composition for asphalt emulsions, cements, grouts, pool plasters, roof coatings and underlayments.

HEALTH AND SAFETY: Refer to the Safety Data Sheet

PACKAGING: 50lb bag, 2000lb pallet

Terms and Conditions of Sale: All statements, technical information and recommendations are based on tests we believe to be reliable, the accuracy or completeness is not guaranteed, and the following is made in place of all warranties, expressed or implied. Our only obligation is to replace product proved to be defective. We shall not be liable for any injury, loss or damage, direct or indirect, from using or not being able to use the product. Before using, customer must determine the suitability of the product for the intended use and customer assumes the responsibility. This statement may not be changed except by an agreement signed by an officer of The R.J. Marshall Company.

October 2017